

NOVADURAN™



Properties	Test Method	Terms	Units	GF Reinforced toughness type
				5010G30TZ
				Improved Thermal Shock Durability
				GF30
Physical properties				
Density	ISO 1183	–	g/cm³	1.50
Dimensional properties				
Moulding shrinkage (2mmt)	–	MD TD	%	0.4 1.0
Rheological properties				
Melt Volume flow Rate	ISO 1133	–	cm³/10min –	8 250°C × 5kg
Mechanical properties				
Yield stress	ISO 527-1,2	–	MPa	–
Stress at break	ISO 527-1,2	–	MPa	115
Strain at break			%	4
Flexural strength	ISO 178	–	MPa	180
Flexural modulus			MPa	8,000
Charpy impact	ISO 179-1, 2	– notched	kJ/m² kJ/m²	64 12
Thermal properties				
Melting temperature	ISO 11357-3	–	°C	224
Temperature of deflection under load	ISO 75-1, 2	1.80MPa 0.45MPa	°C	178 >200
Coefficient of Linear thermal expansion	ISO 11359-2	MD : -30~120°C MD : -30~35°C MD : 35~120°C TD : -30~120°C TD : -30~35°C TD : 35~120°C	1E-5/°C	2.1 2.4 1.8 13.4 9.7 16.1
Flammability	UL94	–	–	HB(0.8mmt) HB(1.5mmt) HB(3mmt) HB(6mmt)
Electrical properties				
Volume resistivity	IEC 60093	–	Ω · m	>1E12
Surface resistivity	IEC 60093	–	Ω	>1E14
Electric strength	IEC 60243-1	1mmt 2mmt 3mmt	MV/m	30 24 –
CTI	UL746A	–	–	PLC1
RTI(Elec)	UL746B	–	–	–
RTI(Imp)	UL746B	–	–	–
RTI(Str)	UL746B	–	–	–
Molding Conditions (Standard example)				
Pre-drying Temperature	–	–	°C	120 / 140
Pre-drying Time	–	–	h	5–8 / 4–6
Cylinder temperature	–	–	°C	240–265
Mold temperature	–	–	°C	50–90
Injection speed	–	–	–	Middle-High
Injection speed	–	–	MPa	20–150
Screw speed	–	–	rpm	80–150

The values described are typical values only.