

Properties	Test Method	Terms	Units	GF Reinforced type
				5010G30
				X4
				Improved Hydrolytic Resistance
GF30				
Physical properties				
Density	ISO 1183	–	g/cm ³	1.53
Dimensional properties				
Moulding shrinkage (2mmt)	–	MD	%	0.4
		TD		1.2
Rheological properties				
Melt Volume flow Rate	ISO 1133	–	cm ³ /10min –	40 250°C × 5kg
Mechanical properties				
Yield stress	ISO 527-1,2	–	MPa	–
Stress at break	ISO 527-1,2	–	MPa	150
Strain at break			%	3
Flexural strength	ISO 178	–	MPa	220
Flexural modulus			MPa	9,100
Charpy impact	ISO 179-1, 2	–	kJ/m ² kJ/m ²	59
		notched		11
Thermal properties				
Melting temperature	ISO 11357-3	–	°C	224
Temperature of deflection under load	ISO 75-1, 2	1.80MPa	°C	>200
		0.45MPa		>200
Coefficient of Linear thermal expansion	ISO 11359-2	MD: -30~120°C	1E-5/°C	1.8
		MD: -30~35°C		2.3
		MD: 35~120°C		2.0
		TD: -30~120°C		11.4
		TD: -30~35°C		7.6
		TD: 35~120°C		14.4
Flammability	UL94	–	–	HB(0.8mmt) HB(1.5mmt) HB(3mmt) HB(6mmt)
Electrical properties				
Volume resistivity	IEC 60093	–	Ω·m	>1E12
Surface resistivity	IEC 60093	–	Ω	>1E14
Electric strength	IEC 60243-1	1mmt	MV/m	27
		2mmt		25
		3mmt		–
CTI	UL746A	–	–	PLC 1
RTI(Elec)	UL746B	–	–	140(0.8mmt BK,WT),140(1.5mmt ALL)
RTI(Imp)	UL746B	–	–	120(0.8mmt BK,WT),120(1.5mmt ALL)
RTI(Str)	UL746B	–	–	140(0.8mmt BK,WT),140(1.5mmt ALL)
Molding Conditions (Standard example)				
Pre-drying Temperature	–	–	°C	120 / 140
Pre-drying Time	–	–	h	5-8 / 4-6
Cylinder temperature	–	–	°C	240-265
Mold temperature	–	–	°C	50-90
Injection speed	–	–	–	Middle-High
Injection pressure	–	–	MPa	20-150
Screw speed	–	–	rpm	80-150

The values described are typical values only.