

Properties	Test Method	Terms	Units	Unreinforced type			
				5010TR			
				XA			
				Impact Modified			
<hr/>							
Physical properties							
Density	ISO 1183	–	g/cm³	1.27			
Dimensional properties							
Moulding shrinkage (2mmt)	–	MD TD	%	1.9 1.8			
Rheological properties							
Melt Volume flow Rate	ISO 1133	–	cm³/10min –	19 250°C × 2.16kg			
Mechanical properties							
Yield stress	ISO 527-1,2	–	MPa	51			
Stress at break	ISO 527-1,2	–	MPa	–			
Strain at break			%	>200			
Flexural strength	ISO 178	–	MPa	77			
Flexural modulus			MPa	2,250			
Charpy impact	ISO 179-1, 2	– notched	kJ/m² kJ/m²	NB 7			
Thermal properties							
Melting temperature	ISO 11357-3	–	°C	224			
Temperature of deflection under load	ISO 75-1, 2	1.80MPa 0.45MPa	°C	65 160			
Coefficient of Linear thermal expansion	ISO 11359-2	MD : -30~120°C MD : -30~35°C MD : 35~120°C TD : -30~120°C TD : -30~35°C TD : 35~120°C	1E-5/°C	11.7 8.0 14.5 12.2 8.8 14.8			
Flammability	UL94	–	–	HB(0.75mmt)			
Electrical properties							
Volume resistivity	IEC 60093	–	Ω · m	>1E12			
Surface resistivity	IEC 60093	–	Ω	>1E14			
Electric strength	IEC 60243-1	1mmt 2mmt 3mmt	MV/m	22 17 –			
CTI	UL746A	–	–	–			
RTI(Elec)	UL746B	–	–	–			
RTI(Imp)	UL746B	–	–	–			
RTI(Str)	UL746B	–	–	–			
Molding Conditions (Standard example)							
Pre-drying Temperature	–	–	°C	120 / 140			
Pre-drying Time	–	–	h	5–8 / 4–6			
Cylinder temperature	–	–	°C	240–265			
Mold temperature	–	–	°C	50–90			
Injection speed	–	–	–	Middle-High			
Injection speed	–	–	MPa	20–150			
Screw speed	–	–	rpm	80–150			

The values described are typical values only.