

Properties	Test Method	Terms	Units	Mineral Reinforced Alloy
				5308FDV K2D
				MD<10
<b>Physical properties</b>				
Density	ISO 1183	–	g/cm³	1.33
<b>Dimensional properties</b>				
Moulding shrinkage (2mmt)	–	MD TD	%	1.6 1.7
<b>Rheological properties</b>				
Melt Volume flow Rate	ISO 1133	–	cm³/10min –	48 265°C × 2.16kg
<b>Mechanical properties</b>				
Yield stress	ISO 527-1,2	–	MPa	–
Stress at break	ISO 527-1,2	–	MPa	60
Strain at break			%	4
Flexural strength	ISO 178	–	MPa	100
Flexural modulus			MPa	2,950
Charpy impact	ISO 179-1, 2	– notched	kJ/m² kJ/m²	75 2
<b>Thermal properties</b>				
Melting temperature	ISO 11357-3	–	°C	255
Temperature of deflection under load	ISO 75-1, 2	1.80MPa 0.45MPa	°C	67 165
Coefficient of Linear thermal expansion	ISO 11359-2	MD : -30~120°C MD : -30~35°C MD : 35~120°C	1E-5/°C	11.0 8.0 13.0
		TD : -30~120°C		11.0
		TD : -30~35°C		8.0
		TD : 35~120°C		13.0
Flammability	UL94	–	–	–
<b>Electrical properties</b>				
Volume resistivity	IEC 60093	–	Ω · m	>1E12
Surface resistivity	IEC 60093	–	Ω	>1E14
Electric strength	IEC 60243-1	1mmt 2mmt 3mmt	MV/m	– – –
				–
				–
CTI	UL746A	–	–	–
RTI(Elec)	UL746B	–	–	–
RTI(Imp)	UL746B	–	–	–
RTI(Str)	UL746B	–	–	–
<b>Molding Conditions (Standard example)</b>				
Pre-drying Temperature	–	–	°C	120 / 140
Pre-drying Time	–	–	h	5-8 / 4-6
Cylinder temperature	–	–	°C	255-275
Mold temperature	–	–	°C	60-120
Injection speed	–	–	–	Middle-High
Injection speed	–	–	MPa	20-150
Screw speed	–	–	rpm	80-150

The values described are typical values only.