

Properties	Test Method	Terms	Units	GF Reinforced type
				5308G30MG
				GF30
				Physical properties
Density	ISO 1183	–	g/cm ³	1.56
Dimensional properties				
Moulding shrinkage (2mmt)	–	MD TD	%	0.3 1.0
Rheological properties				
Melt Volume flow Rate	ISO 1133	–	cm ³ /10min –	47 265°C × 5kg
Mechanical properties				
Yield stress	ISO 527-1,2	–	MPa	–
Stress at break	ISO 527-1,2	–	MPa	150
Strain at break	–	–	%	3
Flexural strength	ISO 178	–	MPa	218
Flexural modulus	–	–	MPa	9,700
Charpy impact	ISO 179-1, 2	– notched	kJ/m ² kJ/m ²	– 8
Thermal properties				
Melting temperature	ISO 11357-3	–	°C	255
Temperature of deflection under load	ISO 75-1, 2	1.80MPa 0.45MPa	°C	190 >200
Coefficient of Linear thermal expansion	ISO 11359-2	MD: -30~120°C	1E-5/°C	–
		MD: -30~35°C		–
		MD: 35~120°C		–
		TD: -30~120°C		–
		TD: -30~35°C TD: 35~120°C		– –
Flammability	UL94	–	–	–
Electrical properties				
Volume resistivity	IEC 60093	–	Ω·m	–
Surface resistivity	IEC 60093	–	Ω	–
Electric strength	IEC 60243-1	1mmt	MV/m	–
		2mmt		–
		3mmt		–
CTI	UL746A	–	–	–
RTI(Elec)	UL746B	–	–	–
RTI(Imp)	UL746B	–	–	–
RTI(Str)	UL746B	–	–	–
Molding Conditions (Standard example)				
Pre-drying Temperature	–	–	°C	120 / 140
Pre-drying Time	–	–	h	5-8 / 4-6
Cylinder temperature	–	–	°C	255-275
Mold temperature	–	–	°C	60-120
Injection speed	–	–	–	Middle-High
Injection pressure	–	–	MPa	20-150
Screw speed	–	–	rpm	80-150

The values described are typical values only.