

Properties	Test Method	Terms	Units	Unreinforced type
				5505S
				Extrusion Improved Flexibility
				—
Physical properties				
Density	ISO 1183	—	g/cm ³	1.28
Dimensional properties				
Moulding shrinkage (2mmt)	—	MD	%	2.2
		TD		2.0
Rheological properties				
Melt Volume flow Rate	ISO 1133	—	cm ³ /10min —	25 250°C × 2.16kg
Mechanical properties				
Yield stress	ISO 527-1,2	—	MPa	28
Stress at break	ISO 527-1,2	—	MPa	—
Strain at break		%	>200	
Flexural strength	ISO 178	—	MPa	31
Flexural modulus		MPa	740	
Charpy impact	ISO 179-1, 2	—	kJ/m ² kJ/m ²	NB
		notched		13
Thermal properties				
Melting temperature	ISO 11357-3	—	°C	222
Temperature of deflection under load	ISO 75-1, 2	1.80MPa	°C	67
		0.45MPa		145
Coefficient of Linear thermal expansion	ISO 11359-2	MD: -30~120°C	1E-5/°C	14.1
		MD: -30~35°C		10.7
		MD: 35~120°C		16.7
		TD: -30~120°C		14.0
		TD: -30~35°C		11.1
		TD: 35~120°C		16.3
Flammability	UL94	—	—	HB(1.5mmt) NA HB(3mmt) NA
Electrical properties				
Volume resistivity	IEC 60093	—	Ω·m	>1E12
Surface resistivity	IEC 60093	—	Ω	>1E14
Electric strength	IEC 60243-1	1mmt	MV/m	22
		2mmt		17
		3mmt		—
CTI	UL746A	—	—	—
RTI(Elec)	UL746B	—	—	—
RTI(Imp)	UL746B	—	—	—
RTI(Str)	UL746B	—	—	—
Molding Conditions (Standard example)				
Pre-drying Temperature	—	—	°C	120 / 140
Pre-drying Time	—	—	h	5-8 / 4-6
Cylinder temperature	—	—	°C	240-265
Mold temperature	—	—	°C	50-90
Injection speed	—	—	—	Middle-High
Injection pressure	—	—	MPa	20-150
Screw speed	—	—	rpm	80-150

The values described are typical values only.