

# NOVADURAN™



Properties	Test Method	Terms	Units	Unreinforced type
				5510S
				Extrusion Highly improved Flexibility
				—
<b>Physical properties</b>				
Density	ISO 1183	—	g/cm³	1.24
<b>Dimensional properties</b>				
Moulding shrinkage (2mmt)	—	MD TD	%	2.2 2.0
<b>Rheological properties</b>				
Melt Volume flow Rate	ISO 1133	—	cm³/10min —	33 250°C × 2.16kg
<b>Mechanical properties</b>				
Yield stress	ISO 527-1,2	—	MPa	21
Stress at break	ISO 527-1,2	—	MPa	—
Strain at break			%	>200
Flexural strength	ISO 178	—	MPa	22
Flexural modulus			MPa	360
Charpy impact	ISO 179-1, 2	— notched	kJ/m² kJ/m²	NB 30
<b>Thermal properties</b>				
Melting temperature	ISO 11357-3	—	°C	219
Temperature of deflection under load	ISO 75-1, 2	1.80MPa 0.45MPa	°C	74 139
Coefficient of Linear thermal expansion	ISO 11359-2	MD : -30~120°C MD : -30~35°C MD : 35~120°C TD : -30~120°C TD : -30~35°C TD : 35~120°C	1E-5/°C	15.5 13.8 16.7 14.6 13.8 16.7
Flammability	UL94	—	—	HB(1.5mmt) NA HB(3mmt NA)
<b>Electrical properties</b>				
Volume resistivity	IEC 60093	—	Ω · m	>1E12
Surface resistivity	IEC 60093	—	Ω	>1E14
Electric strength	IEC 60243-1	1mmt 2mmt 3mmt	MV/m	22 17 —
CTI	UL746A	—	—	—
RTI(Elec)	UL746B	—	—	—
RTI(Imp)	UL746B	—	—	—
RTI(Str)	UL746B	—	—	—
<b>Molding Conditions (Standard example)</b>				
Pre-drying Temperature	—	—	°C	120 / 140
Pre-drying Time	—	—	h	5-8 / 4-6
Cylinder temperature	—	—	°C	240-265
Mold temperature	—	—	°C	50-90
Injection speed	—	—	—	Middle-High
Injection speed	—	—	MPa	20-150
Screw speed	—	—	rpm	80-150

The values described are typical values only.